

Role of Nanopolymers in Advanced Anti-Aging and Regenerative Skincare

Esther Offiong Asuquo^{1,*}, Nworie Felix Sunday² and Stephen Oluwaseyi Ayika³

¹ Department of Industrial Chemistry, University of Cross River State, Calabar 540281, Nigeria

² Department of Industrial Chemistry, Ebonyi State University Abakaliki, Abakaliki 480211, Nigeria

³ Department of Chemistry, Kogi State University, Kabba 272101, Nigeria

* Correspondence: estheroffiong21@gmail.com

How To Cite: Asuquo, E.O.; Sunday, N.F.; Ayika, S.O. Role of Nanopolymers in Advanced Anti-Aging and Regenerative Skincare. *Progress in Composite Materials* **2026**, *2*(1), 1. <https://doi.org/10.53941/pcm.2026.100001>

Received: 14 November 2025

Revised: 26 February 2026

Accepted: 11 May 2026

Published: 26 May 2026

Abstract: The use of nanopolymers in anti-aging and regenerative skincare has emerged as a transformative advancement in dermatological science. Specific nanopolymeric systems such as chitosan nanoparticles, hyaluronic acid nanogels, poly(lactic-co-glycolic acid) (PLGA) nanospheres, dendrimers, and polymeric micelles have demonstrated significant potential in enhancing topical delivery and skin regeneration. These nanoscale polymers (1–100 nm) offer tunable physicochemical properties that enable efficient encapsulation, targeted delivery, and controlled release of active ingredients, including retinoids, peptides, antioxidants, and growth factors. Their small size and surface modifiability improve penetration across the stratum corneum and facilitate interaction with dermal fibroblasts, promoting collagen synthesis, enhanced hydration, and cellular renewal. In anti-aging applications, nanopolymers reduce wrinkles, fine lines, and hyperpigmentation by improving bioavailability and stability of sensitive compounds such as vitamins and retinoids. In regenerative dermatology, nanopolymeric scaffolds and nanocarriers support wound healing, angiogenesis, and extracellular matrix remodeling. Despite their promising benefits, concerns regarding long-term safety, regulatory frameworks, and production scalability remain. Continued research into biodegradable and biocompatible nanopolymers is expected to further advance personalized and precision skincare strategies. This review highlights the mechanistic roles and therapeutic potential of nanopolymers in reshaping modern anti-aging and regenerative skincare.

Keywords: nanopolymers; anti-aging skincare; regenerative cosmetics; nanotechnology in dermatology; controlled drug delivery; skin rejuvenation

1. Introduction

Skin aging is a complex, gradual process influenced by both intrinsic (chronological) and extrinsic (environmental) factors [1]. It is characterized by a decline in the skin's structural integrity and physiological function, leading to visible signs such as wrinkles, sagging, dryness, and pigmentation [2]. Intrinsic aging refers to the natural aging process determined largely by genetic factors and the biological clock of our cells [3]. Over time, this leads to reduced activity of fibroblasts, cells responsible for producing collagen and elastin, resulting in diminished structural support within the skin. Consequently, there is a decline in collagen and elastin production, thinning of both the epidermis and dermis layers, slower cellular turnover, and a reduced ability for the skin to repair itself [4]. In contrast, extrinsic aging is driven by environmental and lifestyle-related factors, such as prolonged exposure to ultraviolet (UV) radiation (photoaging), pollution, smoking, poor nutrition, and chronic stress [5]. These external stressors accelerate the production of free radicals, leading to oxidative stress and



inflammation, which in turn cause DNA damage, degrade collagen, and reduce skin elasticity, significantly contributing to premature aging [6].

The skin's regenerative capacity is a fundamental aspect of its resilience and ability to maintain health and appearance over time [7]. Even as it endures daily environmental stress and the inevitable progression of aging, the skin remains capable of self-renewal and repair when properly maintained. At the cellular level, keratinocytes in the basal layer of the epidermis continuously divide and migrate upward to replenish the outer skin layer, ensuring a consistent turnover. Simultaneously, fibroblasts in the dermis produce critical extracellular matrix (ECM) components, such as collagen and hyaluronic acid, which provide structure, hydration, and elasticity [8]. Angiogenesis, the process of forming new blood vessels, supplies essential nutrients and oxygen to maintain tissue vitality, while the intricate wound healing process unfolds through coordinated phases of inflammation, proliferation, and tissue remodeling to restore skin integrity after injury [9]. However, this intrinsic regenerative ability gradually diminishes with age, resulting in slower wound healing, reduced cellular turnover, and a decline in the production of ECM components [10]. To counteract these changes, scientific advancements have introduced external interventions aimed at stimulating and supporting skin regeneration. Therapeutic agents such as growth factors and bioactive peptides are formulated to mimic or enhance natural signaling pathways that drive cellular repair and renewal. More recently, the integration of nanotechnology in skincare and dermatological treatments has allowed for the precise delivery of these active compounds to target cells, thereby improving their efficacy. These innovations hold promise in not only mitigating the effects of aging but also in revitalizing the skin's capacity to heal and regenerate [11].

Composite Nanopolymer Technologies (CNT) represent an advanced class of engineered systems that integrate multiple polymeric components at the nanoscale to achieve enhanced functionality. In dermatological applications, CNT platforms are uniquely positioned to overcome the limitations of conventional formulations by enabling controlled delivery, improved stability, and targeted interaction with skin structures [12].

Composite Nanopolymer Technologies (CNT) are defined as advanced nanoscale systems that integrate two or more polymeric or polymer-inorganic components to achieve enhanced or multifunctional performance. These systems include polymer-nanofiller composites, multilayered nanohybrids, crosslinked polymeric networks with embedded functional agents, and stimulus-responsive nanocomposites. Unlike conventional nanopolymer-based systems that may rely on a single polymer matrix, CNT platforms are specifically engineered to combine structural, physicochemical, and biological functionalities within a unified system [13]. This distinction is critical, as CNTs enable synergistic effects such as improved mechanical stability, controlled release behavior, targeted delivery, and enhanced interaction with biological tissues, making them particularly suitable for advanced dermatological applications.

Tunable particle size, surface functionality, polymer composition, and responsiveness to physiological stimuli are key design principles of CNT that directly influence their dermatological performance. These properties enable improved penetration through the stratum corneum, sustained release of bioactive compounds, enhanced collagen synthesis, and protection against oxidative stress, thereby contributing to anti-aging and regenerative outcomes [14].

Regenerative medicine represents a transformative approach in dermatology, focusing on repairing, replacing, or regenerating cells, tissues, and organs to restore or establish normal function [15]. The potential applications of regenerative medicine in dermatology are vast, ranging from wound healing and scar reduction to the treatment of chronic skin conditions and aesthetic enhancements (Figure 1).

The skin possesses an inherent ability to regenerate through stem cells and biological signaling pathways, allowing for routine repair and maintenance. However, this natural capacity diminishes with age and may be inadequate in cases of severe injury or chronic skin conditions. Regenerative medicine aims to bolster or replace these natural healing mechanisms using advanced therapies to improve repair and recovery outcomes [16].

Regenerative medicine in dermatology revolves around three main strategies: stem cell therapy, tissue engineering, and biomaterials. Stem cells possess the unique ability to differentiate into specialized cell types, making them useful for skin regeneration and repair. Tissue engineering focuses on creating biological substitutes to restore skin function, while biomaterials are designed to support and enhance the healing process through interactions with the body. Together, these technologies offer innovative solutions for managing various skin conditions [17].

Stem cell therapy has emerged as a particularly promising approach for dermatological issues. Adult stem cells, particularly mesenchymal stem cells (MSCs), have demonstrated the ability to accelerate wound healing and reduce inflammation. These cells are typically harvested from sources like bone marrow and fat tissue [18]. Although embryonic stem cells (ESCs) and induced pluripotent stem cells (iPSCs) offer broader differentiation potential, concerns around ethics and safety, including the risk of tumor formation, currently limit their clinical use.




Figure 1. The potential applications of regenerative medicine in dermatology.

Tissue engineering in dermatology combines cells, scaffolds, and bioactive molecules to produce skin substitutes capable of replacing damaged tissue [19]. These substitutes are designed to integrate seamlessly with the patient's existing skin. Advanced techniques like bioprinting allow for the precise construction of layered skin structures, mimicking the complexity of natural skin and offering future potential in burn and ulcer treatment. Meanwhile, biomaterials like hydrogels play a critical supportive role by providing structural integrity, delivering therapeutic agents, and maintaining environments favorable for cell growth and wound healing [20].

Clinical applications of regenerative dermatology include improved wound healing, scar reduction, treatment of chronic skin conditions, and aesthetic enhancements [21]. Stem cell therapies have shown benefits in managing chronic wounds by stimulating new tissue and blood vessel formation. Engineered tissues and antifibrotic treatments aim to reduce scarring. In conditions like psoriasis, regenerative methods target the underlying immune dysfunction. Aesthetically, procedures like fat grafting enriched with regenerative cells offer natural-looking facial rejuvenation.

Regenerative medicine plays a transformative role in dermatology by offering advanced treatments for both aesthetic enhancement and clinical skin repair. In anti-aging and cosmetic applications, it promotes collagen production, reduces wrinkles and pigmentation, and improves skin hydration and texture [22]. For wound healing, therapies like stem cells and bioengineered skin accelerate tissue repair through angiogenesis and re-epithelialization. Cutting-edge technologies, including stem cell therapy, growth factors, and scaffold materials, support skin regeneration at the cellular level [23]. When combined with traditional dermatological procedures, these regenerative approaches enhance outcomes, can be personalized to individual needs, and show promise in treating disorders like vitiligo and eczema. Notably, many of these treatments are minimally invasive, offering lasting results with quicker recovery and fewer side effects.

This review focuses on the role of Composite Nanopolymer Technologies in anti-aging and regenerative dermatology. It first discusses the fundamental principles and classifications of CNT systems, followed by an overview of their mechanisms of action in skin applications. Subsequently, specific nanopolymeric platforms and their dermatological applications are examined. The review also addresses safety considerations, limitations, and environmental implications, and concludes with future perspectives for CNT-driven personalized skincare.

2. The Emergence of Nanotechnology in Dermatology

Nanotechnology has significantly transformed dermatology, particularly through the development of polymeric nanocarriers designed to enhance topical and transdermal drug delivery. Among the most relevant

nanopolymeric systems in dermatological applications are chitosan nanoparticles, poly(lactic-co-glycolic acid) (PLGA) nanospheres, hyaluronic acid-based nanogels, polymeric micelles, dendrimers, and electrospun polymeric nanofibers [24–26]. These systems possess tunable physicochemical properties, including surface charge, particle size, biodegradability, and controlled release capability, which make them highly suitable for targeted skin applications.

For example, chitosan nanoparticles, due to their polycationic nature, enhance adhesion to the negatively charged skin surface and improve penetration through the stratum corneum while providing intrinsic antimicrobial activity [27]. Similarly, PLGA nanospheres and nanocapsules are widely employed for encapsulating unstable active ingredients such as retinoids and antioxidants, enabling sustained release and improved stability [28]. Hyaluronic acid nanogels are particularly valuable in anti-aging formulations because of their natural presence in skin tissue and their ability to enhance hydration and dermal delivery [29–31]. Nanoemulsion systems treat conditions like psoriasis, acne, and skin cancers, and help minimize side effects, such as skin atrophy, through nanoencapsulation of corticosteroids [32].

Polymeric micelles, formed from amphiphilic block copolymers, provide hydrophobic cores capable of solubilizing poorly water-soluble compounds, thereby improving the bioavailability of actives such as vitamins and phytochemicals [33]. Dendrimers, characterized by their highly branched architecture, allow precise control over drug loading and surface functionalization for targeted delivery to specific skin layers [28]. Additionally, electrospun nanofibrous scaffolds composed of biodegradable polymers such as PLGA, collagen, or chitosan are increasingly applied in regenerative dermatology for wound healing and extracellular matrix mimicry [34,35].

Other reported applications of nanopolymers include: the use of silica-gold nanoshells for treating basal cell carcinoma, offering a more precise and less damaging approach compared to traditional therapies [36], nanocapsules carrying active ingredients like retinol and vitamin C enhance the performance of anti-aging creams by allowing deeper penetration into the skin [37], nano-sized titanium dioxide and zinc oxide provide effective UV protection without leaving a visible white residue in sunscreens, improving both efficacy and aesthetic appeal [38,39].

2.1. Physicochemical Properties of Nanopolymers Relevant to Skincare

The integration of nanotechnology into cosmetics and skincare has expanded significantly, with nanopolymers emerging as key materials due to their unique properties and broad applications. These materials enhance the delivery and stability of active ingredients and enable the development of innovative product textures, addressing the limitations of traditional formulations. The rise of nano cosmeceuticals reflects the growing demand for technologically advanced skincare solutions.

A wide range of nano systems, including liposomes, nanoemulsions, and various nanoparticles, are employed in cosmetics, categorized by their chemical composition into carbon-based, inorganic, organic, and composite materials. The main types include lipid-based, polymeric, and inorganic nanoparticles [25,40]. These materials are further classified as soluble/biodegradable or insoluble/biopersistent, a distinction crucial for risk assessment and regulatory evaluation. The diversity of nanomaterials highlights the interdisciplinary nature of cosmetic innovation and underscores the need for tailored safety assessments based on nanoparticle behavior in biological systems [26]. Nanopolymers, a significant subset of nanomaterials, can be broadly classified into natural and synthetic categories, each with unique properties and applications in skincare (Figure 2).

Natural polymeric nanocarriers, particularly chitosan-based systems, offer biocompatibility, biodegradability, and moisturizing properties, making them highly suitable for skincare applications [27]. Chitosan nanocarriers effectively deliver active ingredients like retinol, with their safety and modifiability enhancing their cosmetic appeal. Their natural origin aligns with the growing consumer demand for “clean beauty” products focused on safety and efficacy [41]. Hyaluronic acid (HA) is a biocompatible, biodegradable nanopolymer widely recognized for its moisturizing and anti-aging benefits in skincare. Formulations often incorporate HA of varying molecular weights to target multiple layers of skin hydration and enhance natural defense mechanisms. Given its natural presence in the skin, HA is perceived as safe and is highly favored by consumers, a preference reinforced by advancements in nanotechnology [30].

Other relevant polymeric systems include polymeric micelles, which are formed by amphiphilic polymers in aqueous solutions, creating a hydrophobic core suitable for delivering poorly water-soluble drugs [33]. The hydrophilic shell, often composed of polyethylene glycol (PEG), enhances the stability of these micelles and prevents their aggregation. Polymeric micelles exhibit the potential for prolonged circulation time within the body and targeted delivery of encapsulated compounds. This capability offers a solution for incorporating poorly water-soluble active ingredients into skincare formulations, thereby enhancing their bioavailability and overall efficacy. Many potentially beneficial skincare ingredients have limited solubility in water, which restricts their use. Polymeric micelles address this challenge by encapsulating these ingredients in a manner that allows for their

effective delivery to the skin. Nanofibers, produced from polymers through techniques like electrospinning, represent another class of nanopolymers with applications in skincare. They offer the potential for prolonged release of loaded compounds and are utilized in tissue engineering and wound healing applications. Cosmeceutical tissues made from chitin nanofibrils and nanolignin serve as examples of nanofibers in skincare [42].




Figure 2. Classification of nanopolymers used in cosmetic and dermatological applications, including natural nanopolymers (e.g., chitosan and hyaluronic acid) and synthetic nanopolymers (e.g., PLGA and PEG-based systems), highlighting their functional roles in skincare formulations.

Specific nanopolymers demonstrate diverse functional roles in skincare applications. For example, chitosan nanoparticles facilitate the delivery of retinol and other hydrophobic actives for anti-wrinkle and anti-acne formulations due to their penetration-enhancing and antimicrobial properties. Hyaluronic acid-based nanopolymers provide deep hydration, improve dermal elasticity, and support extracellular matrix integrity. Polymeric nanospheres and nanocapsules are widely employed for the controlled release of antioxidants, vitamins, and peptides, improving their stability and bioavailability.

These nanopolymeric systems have been incorporated into commercially available cosmetic and cosmeceutical formulations; however, their scientific value lies in their physicochemical characteristics, including

encapsulation efficiency, sustained release behavior, and enhanced dermal penetration. The performance of these systems depends primarily on polymer composition, molecular weight, surface charge, and particle size rather than brand-specific formulation.

Carbopol primarily functions as a thickener, stabilizer, and gelling agent, contributing to the desired texture and consistency of creams, lotions, and gels, which indirectly supports the delivery and application of other active ingredients. The diverse roles of nanopolymers in skincare extend beyond simply acting as carriers for active ingredients; they also play crucial roles in ensuring formulation stability, enhancing product texture, and providing a sustained effect on the skin. The unique physicochemical properties of these materials enable them to actively contribute to the overall performance and sensory experience of skincare products.

2.2. Nanopolymers and Skin Penetration Enhancement

The delivery of therapeutic and cosmetic agents through the skin has garnered significant attention due to its non-invasive nature and the potential for targeted action, minimizing systemic side effects associated with oral or injectable routes. Topical and transdermal delivery systems offer advantages such as bypassing first-pass metabolism in the liver and providing localized treatment [43]. However, the skin, particularly its outermost layer, the stratum corneum, presents a formidable barrier that restricts the penetration of most substances. To overcome this challenge, nanotechnology, and specifically the use of nanopolymers, has emerged as a promising strategy to enhance the penetration of active ingredients into and through the skin.

The unique properties of nanopolymers are pivotal in their ability to enhance skin penetration. Their diminutive size allows them to potentially pass through the tight junctions between skin cells and access skin appendages like hair follicles [44]. The large surface area inherent to nanoparticles facilitates extensive interaction with the skin's surface and can significantly improve the loading and subsequent release of active ingredients. Moreover, the surface charge of nanopolymers can be precisely engineered to influence their interaction with the predominantly negatively charged skin surface. A key advantage is their capacity to encapsulate both hydrophilic and hydrophobic drugs, thereby enhancing the delivery of a broader spectrum of active molecules. Additionally, nanopolymers can be designed to exhibit controlled and sustained release profiles, which can prolong the therapeutic effects of the delivered agents and reduce the frequency of application [44]. This adaptability in their properties makes nanopolymers exceptionally suitable for overcoming the skin's barrier function and improving the efficacy of topical formulations.

The skin, the body's largest organ, is a multi-layered structure consisting of the outermost epidermis, the supportive dermis beneath it, and the deepest hypodermis for insulation and energy storage. Crucially, the top layer of the epidermis, known as the stratum corneum, serves as the skin's principal barrier. The stratum corneum is a highly organized layer structure composed of dead keratinocytes (also called corneocytes, or the 'bricks') embedded in a complex extracellular lipid matrix (the 'mortar'), which collectively regulates water loss, prevents microbial penetration, and acts as a shield against environmental stressors. This 'bricks and mortar' architecture is responsible for the skin's selective permeability, primarily allowing small, lipophilic molecules to pass while preventing the entry of larger or hydrophilic substances, a barrier integrity that is paramount when considering the topical application and effective penetration of materials like nanopolymers [44].

Certain nanopolymers can enhance skin penetration by interacting with and transiently disrupting the highly ordered lipid bilayers of the stratum corneum (Table 1). This disruption can lead to increased permeability by creating temporary gaps or fluidizing the lipid structure, allowing both the nanopolymer and its encapsulated cargo to pass through more easily [44]. For instance, components of the nanopolymer with an affinity for lipids can intercalate into the lipid bilayer, altering its organization and reducing its barrier function. This mechanism underscores the importance of the chemical composition and surface properties of the nanopolymer in facilitating its interaction with the skin's lipid components.

Surface modifications on nanopolymers can play a crucial role in enhancing their interaction with corneocytes, potentially facilitating their passage directly through these cells. This transcellular transport can occur through various mechanisms, including the binding of specific ligands on the nanopolymer surface to receptors present on the corneocyte membrane, which can trigger endocytosis or other cellular uptake processes [45]. Additionally, some nanopolymers may alter the fluidity of the corneocyte cell membrane, making it easier to traverse (Table 1). This pathway, while challenging due to the dense keratin network within corneocytes, can be significantly enhanced by the tailored design of the nanopolymer surface.

The follicular pathway offers a significant route for nanopolymers to bypass the dense stratum corneum and penetrate deeper into the skin. The size of the nanopolymer is a critical determinant for effective follicular penetration.

Table 1. Examples of Nanopolymers and Their Mechanism of Action in Skin Penetration.

| Nanopolymer Type | Active Ingredient (Example) | Application (Example) | Mechanism of Action (Based on Snippets) | References |
|--------------------------|--|---|---|------------|
| Chitosan Nanoparticles | Retinol, Cinnarizine, β -Arbutin | Anti-aging, Enhanced Delivery, Skin Whitening | Polycationic nature interacts with negatively charged skin, alters stratum corneum protein structure, acts on tight junctions, increases water content. | [27] |
| Hyaluronic Acid NPs | Hyaluronic Acid, Other Actives | Hydration, Anti-aging | Nanoparticulate form allows deeper penetration compared to free HA, grafting with fatty acids enhances transcellular transport, sustained release. | [46] |
| Solid Lipid NPs (SLNs) | Vitamin A | Anti-wrinkle | Enhanced penetration, protects internal compounds from degradation, occlusive properties aid hydration. | [27] |
| Nanoemulsions (NEs) | Paclitaxel, Caffeine | Psoriasis, Enhanced Delivery | Increase concentration gradient, interact with stratum corneum lipids, presence of surfactants as permeation enhancers. | [44] |
| Polymeric Micelles | Bevacizumab, Dexamethasone | Ocular Applications | Stabilize and solubilize drugs, enhance cellular uptake and tissue penetration (application extended to skin penetration in other snippets). | [47] |
| Polymeric Nanohydrogels | Various Drugs | Topical Drug Delivery | Versatile drug loading, controlled release, enhanced skin penetration. | [13] |
| Patented HLG Nanopolymer | Hyaluronic Acid, PGA, Lysine | Hydration, Anti-aging | Promotes sustained and prolonged release of active ingredients, long-lasting hydrating effect, enhances transport of ingredients. | [48] |

2.3. Research Findings on the Success of Nanopolymers in Promoting Skin Penetration

Numerous *in vitro* studies have provided substantial evidence for the effectiveness of nanopolymers in enhancing skin penetration. Permeation studies utilizing Franz diffusion cells, a standard method for assessing percutaneous absorption, have demonstrated that drug-loaded nanopolymers can significantly increase the amount of active ingredient that permeates through excised skin compared to conventional formulations. Confocal microscopy, a powerful imaging technique, allows for the visualization of fluorescently labeled nanopolymers as they penetrate into different layers of the skin, providing direct evidence of their ability to traverse the skin barrier [46]. Furthermore, studies have shown that encapsulating drugs within nanopolymers can enhance their solubility and stability, ensuring that a higher concentration of the active compound is available for penetration. These *in vitro* findings collectively support the notion that nanopolymers can effectively overcome the skin's barrier properties and facilitate the delivery of active ingredients.

In vivo studies, primarily conducted on animal models, have further validated the effectiveness of nanopolymers in enhancing skin penetration and improving therapeutic outcomes. For example, studies on rats have shown that nanoparticle formulations of non-steroidal anti-inflammatory drugs (NSAIDs) exhibit significantly higher skin penetration and retention, leading to enhanced anti-inflammatory activity compared to conventional bulk-drug formulations [46]. Research using fluorescently labeled gold nanoparticles in rats has demonstrated that nanoparticles with a size of 100 nm can diffuse through hair follicles, reaching deeper skin layers. Additionally, *in vivo* studies on mice have shown that hyaluronic acid nanoparticles can deliver hyaluronic acid into the dermis, reducing transepidermal water loss caused by UV irradiation, an effect not observed with free hyaluronic acid [31]. The successful induction of hair growth in mice using cyclosporin A-loaded chitosan nanocapsules further highlights the potential of nanopolymers for targeted drug delivery to specific skin structures. These *in vivo* findings provide critical evidence of the therapeutic potential of nanopolymers in dermatological applications.

3. Nanopolymers in Anti-Aging Applications

The process of aging is a multifaceted biological phenomenon that encompasses a gradual deterioration of physiological functions over time (Figure 3). This complex process is influenced by a combination of intrinsic and extrinsic factors. The skin's outermost layer, the stratum corneum (SC), presents a formidable barrier that limits the penetration of most topically applied substances. This barrier function is essential for protecting the body from external threats, but it also hinders the delivery of cosmetic ingredients designed to target deeper skin layers. Nanoparticles, including nanopolymers, can overcome this barrier through several pathways such as the

intercellular, transcellular and follicular pathways [49]. The intercellular pathway involves the passage of nanoparticles through the lipid-rich matrix that exists between skin cells. The transcellular pathway allows nanoparticles to move directly through the skin cells themselves. Additionally, the follicular pathway provides another route of penetration, where nanoparticles can enter the skin through hair follicles, which can act as reservoirs for these tiny delivery systems. This enhanced penetration capability allows nanopolymers to deliver active anti-aging ingredients beyond the superficial layers of the skin, reaching the target sites where they can exert their effects. Furthermore, nanopolymers can be specifically designed to target particular skin structures or cell types.




Figure 3. Causes of skin aging and the role of nanopolymers in anti-aging applications.

For instance, nanopolymers can be engineered to preferentially interact with fibroblasts in the dermis, which are responsible for the production of collagen and elastin, or with melanocytes in the epidermis, which are involved in the production of melanin and contribute to skin pigmentation. This targeted delivery maximizes the impact of anti-aging ingredients at the precise location where they are needed most.

3.1. Delivery of Active Ingredients (e.g., Retinoids, Peptides, Antioxidants)

Various types of nanopolymers are employed in cosmetic anti-aging formulations to achieve enhanced delivery and targeting effects. Polymeric nanoparticles, including both nanospheres and nanocapsules, are widely used for the encapsulation and controlled release of a variety of anti-aging active ingredients such as antioxidants (e.g., Vitamin C, Vitamin E), retinoids, and peptides [28]. Nanocapsules, characterized by a liquid core surrounded by a polymeric shell, are particularly effective for providing sustained release of encapsulated drugs. In contrast, nanospheres consist of a solid polymeric matrix within which active substances can be dispersed or stored. For example, poly(lactic-co-glycolic acid) (PLGA) nanospheres loaded with Vitamin C have been shown to promote collagen production and exert antioxidant effects in the skin. Liposomes and niosomes are other important classes of nanocarriers used in cosmetic anti-aging products. Liposomes are nanoscale vesicles composed of a phospholipid bilayer, similar to the membranes of biological cells, and are capable of delivering both hydrophilic (water-soluble) and hydrophobic (lipid-soluble) active ingredients. Niosomes are structurally similar vesicle-like systems but are made from non-ionic surface-active agents [28]. Both liposomes and niosomes are biocompatible and enhance the penetration of encapsulated anti-aging compounds, such as vitamins and peptides, to improve skin hydration and reduce the appearance of wrinkles.

Nanoemulsions are fine emulsions with extremely small droplet sizes, typically less than 100 nanometers, which offer improved stability, a transparent appearance, and a pleasant feel on the skin [28]. These nanoemulsions can effectively enhance the penetration of a wide range of active anti-aging ingredients, including both water-

soluble and oil-soluble compounds. For instance, nanoemulsions of grapeseed oil are used for their antioxidant and anti-aging properties.

Nanofibers, which are ultra-thin polymer fibers with diameters in the nanometer range, are produced using techniques like electrospinning. These nanofibers are finding applications in cosmetic masks, where they can facilitate the transdermal delivery of active ingredients due to their high surface area and unique texture. An example includes biodegradable nanofiber masks infused with hyaluronic acid, designed to provide long-lasting skin hydration. Finally, dendrimers are spherical, highly branched polymeric nanocarriers with a well-defined size and structure. Their unique structure allows them to encapsulate active molecules within their interior or have them attached to their surface, enabling targeted delivery to specific skin cells or layers. For example, dendrimers have been shown to enhance the loading and skin penetration of resveratrol, a potent antioxidant with anti-aging properties.

3.2. Enhanced Penetration and Targeted Release

Another crucial benefit of using nanopolymers is their capacity for controlled or targeted release, which allows for prolonged action of the anti-aging compounds. Nanopolymer-based delivery systems can be engineered to release their encapsulated therapeutic agents over extended periods, thereby maintaining therapeutic concentrations at the target site and reducing the frequency of application required [48]. This sustained release not only improves the convenience and patient compliance with treatment regimens but can also lead to a more consistent and prolonged therapeutic effect, ultimately enhancing the overall outcome of anti-aging interventions. Furthermore, the development of stimuli-responsive nanopolymers takes controlled release a step further by enabling the on-demand release of active ingredients in response to specific triggers present at the target site. This level of precision allows for highly targeted and localized action, maximizing the therapeutic benefit while minimizing potential side effects.

3.3. Prolonged Stability and Bioavailability

Nanopolymers offer improved stability and protection of active ingredients. Many anti-aging molecules, such as antioxidants, peptides, and retinoids, are inherently unstable and prone to degradation when exposed to environmental factors like light, enzymes, or oxidation. Nanopolymers can encapsulate these sensitive compounds, effectively shielding them from these degradation pathways and ensuring that they remain potent throughout the product's shelf life and during application. This protection is crucial for maintaining the efficacy of the delivered anti-aging compounds and ensuring that they can exert their intended effects upon reaching their target [48].

The effectiveness of nanopolymers in achieving anti-aging effects has been the subject of extensive investigation in scientific literature. Numerous *in vitro* studies, conducted on cell cultures, and *in vivo* studies, performed on animal models, have demonstrated the potential of nanopolymers to enhance the delivery and overall efficacy of a wide range of anti-aging compounds. These studies have often reported improvements in key indicators of skin aging, such as enhanced skin hydration, increased elasticity, and a noticeable reduction in the appearance of wrinkles and hyperpigmentation. Importantly, clinical trials, which involve testing these nanopolymer-based anti-aging treatments on human participants, are increasingly being conducted. Some of these trials have shown promising results in alleviating wrinkles and other visible signs of aging [28,48].

Expert opinions within the scientific and dermatological communities generally acknowledge the significant potential of nanopolymers to enhance the effectiveness of both cosmetic and medical anti-aging interventions [50]. There is a broad consensus that the unique properties of nanopolymers, such as their ability to improve penetration and enable targeted delivery of active ingredients, offer substantial advantages over traditional formulations. However, some experts also express ongoing concerns regarding the potential risks associated with the long-term use and the ability of certain nanoparticles to penetrate the skin barrier [51]. This highlights the continued need for thorough safety assessments and a comprehensive understanding of the potential long-term impacts of these materials. Dermatologists often advise a balanced approach to anti-aging, typically recommending foundational strategies such as consistent sunscreen use and regular moisturizing before considering products with more specialized active ingredients, including those delivered through nanotechnology.

The long-term effects and overall safety profile of nanopolymers used in anti-aging applications remain areas of active research and ongoing evaluation. While many nanopolymers are designed to be biocompatible and biodegradable, facilitating their safe use and elimination from the body, the long-term consequences of their use, particularly with repeated application over many years, are still being investigated [51]. Some studies have raised concerns about the potential for certain nanoparticles to induce oxidative stress, trigger inflammation, and even cause DNA damage. The biodegradability of many nanopolymers is a significant advantage in terms of long-term safety, as it allows for their breakdown and eventual clearance from the body, potentially mitigating some of these

concerns. However, continued research and robust safety evaluations are essential to fully understand the long-term impact of nanopolymers and ensure their safe and responsible use in anti-aging products.

4. Nanopolymers in Regenerative Skin Therapy

Regenerative skin therapy is an evolving field dedicated to the repair, rejuvenation, replacement, or regeneration of skin tissues with the ultimate goal of restoring their normal function and aesthetic appearance. The primary objectives of this therapeutic area encompass several key aspects. Wound healing is a central focus, aiming to accelerate the closure of both acute and chronic wounds, minimize the formation of disfiguring scars, and fully restore the skin's protective barrier. Another crucial objective is skin rejuvenation, which involves reversing or slowing down the visible signs of aging, such as the appearance of wrinkles, the loss of skin elasticity, and the development of pigmentation irregularities. Furthermore, regenerative skin therapy seeks to provide effective treatments for a variety of skin disorders, including burns, scars resulting from injury or surgery, chronic ulcers that are difficult to heal, and even genetic disorders that manifest in the skin [34].

Conventional therapeutic approaches for addressing skin regeneration needs have traditionally included the use of basic wound dressings to protect the injured area, the application of growth factors to stimulate cellular activity, and skin grafts to replace large areas of damaged skin [34]. However, the field has advanced significantly, with the emergence of innovative regenerative approaches. These include stem cell therapy, which utilizes the unique ability of stem cells to differentiate into various skin cell types to promote regeneration. Bioengineered skin substitutes represent another advanced approach, offering lab-grown skin tissues that can replace damaged skin. Platelet-rich plasma (PRP) therapy, which involves using a concentration of the patient's own platelets rich in growth factors, has shown promise in enhancing wound healing and skin rejuvenation.

Exosome-based therapies, utilizing nanosized vesicles secreted by cells, are being explored for their potential to stimulate cell regeneration and improve skin health. Gene editing techniques, such as CRISPR, hold potential for correcting genetic defects affecting the skin. Additionally, various laser treatments and microneedling procedures are employed to stimulate collagen production and improve skin texture and appearance. More recently, 3D bioprinting has emerged as a cutting-edge technology for creating artificial tissues and organs, including skin grafts, by depositing living cells and biomaterials layer by layer [52]. An interesting area within regenerative medicine is regenerative aesthetics, which focuses on utilizing treatments and procedures that not only enhance physical appearance but also stimulate the body's natural healing and regeneration processes, often leveraging the body's own resources like PRP or stem cells. The earliest applications of regenerative medicine for skin can be traced back to the use of synthetic skin in grafting procedures for burn victims, highlighting the long-standing interest in harnessing the body's regenerative capabilities for skin repair [53].

4.1. Skin Repair and Wound Healing

Nanopolymers play a multifaceted role in promoting effective wound healing. They can contribute to a favorable healing environment by forming a protective barrier against external contaminants, thus reducing the risk of infection, and by maintaining an optimal level of moisture at the wound site, which is crucial for cellular processes involved in tissue repair. Certain nanopolymers, particularly when incorporated with antimicrobial agents, exhibit direct antibacterial properties (Table 2).

For instance, silver nanoparticles, when integrated into nanopolymeric matrices, can effectively combat microbial colonization. The mechanisms of action for these nanocomposites often involve disrupting bacterial cell membranes, interfering with DNA synthesis, and inducing oxidative stress [54].

Nanopolymeric scaffolds, especially in the form of nanofibers, are designed to mimic the intricate structure of the skin's extracellular matrix (ECM). This structural similarity is vital as it provides a framework that encourages cells, such as fibroblasts and keratinocytes, to adhere, migrate, proliferate, and ultimately regenerate new tissue. A specific example of this is the use of electrospun nanofibers composed of a blend of PLGA and silk fibroin, which have demonstrated enhanced attachment and proliferation of fibroblasts, leading to improved healing outcomes in diabetic wounds.

Furthermore, nanopolymers serve as excellent vehicles for the controlled release of growth factors and other therapeutic agents directly to the wound site. This localized and sustained delivery can significantly accelerate the healing process. For example, PLGA nanoparticles loaded with vascular endothelial growth factor (VEGF) have been shown to promote angiogenesis, a critical step in wound healing [34].

Table 2. Common Nanopolymers and their Specific Actions in Skin Repair and Wound Healing.

| Nanopolymer System | Structural Class | Therapeutic Agent | Mechanism of Action | Application | References |
|--|--|--------------------------|--|--------------------------------------|------------|
| Silver nanoparticles in polymeric matrix | Nanocomposite (inorganic–polymer hybrid) | Silver (Ag) | Antimicrobial activity via membrane disruption, ROS generation | Wound healing, infection control | [34,54] |
| Chitosan nanoparticles | Natural polymer | Antibiotics, bioactives | Antimicrobial, hemostatic, enhances cell adhesion | Wound healing, infection prevention | [55,56] |
| PLGA nanoparticles | Synthetic polymer | VEGF, EGF | Controlled release, promotes angiogenesis | Tissue regeneration, wound healing | [34] |
| Collagen nanofibers | Natural polymer | — | ECM mimicry, enhances cell adhesion and proliferation | Skin grafts, tissue engineering | [57] |
| Alginate/gelatin hydrogels | Natural polymer composite | — | Fluid absorption, supports cell growth | Wound healing | [58] |
| Dendrimers | Synthetic branched polymer | siRNA, genes | Targeted delivery, high loading capacity | Gene therapy, regenerative treatment | [34] |
| Liposomes | Lipid-based nanocarrier | Various drugs | Enhanced penetration, biocompatibility | Drug delivery, skin treatment | [44] |
| Nanogels | Hydrogel polymer | Anti-inflammatory agents | Stimuli-responsive, controlled release | Localized inflammation control | [44] |

Collagen-based nanopolymers have also emerged as promising materials in wound healing applications due to their inherent biocompatibility and biodegradability [54]. Similarly, chitosan nanopolymers are utilized in wound dressings for their natural antimicrobial and hemostatic properties, aiding in infection prevention and blood clotting [55]. Beyond promoting healing, nanopolymers are also being explored for their ability to minimize scar formation and improve the overall aesthetic outcome of the healed wound.

The combination of nanopolymers with plant extracts, which possess antioxidant, anti-inflammatory, and antimicrobial properties, can lead to a synergistic effect, further enhancing the wound healing process [59]. Moreover, nanopolymers can be engineered to respond to specific cues within the wound microenvironment, such as changes in pH or the presence of certain enzymes, to release their therapeutic payload on demand, offering a more targeted and efficient approach to healing. While silver nanoparticles are recognized for their potent antimicrobial properties in wound care, their potential for cytotoxicity at higher concentrations necessitates careful consideration of dosage and the exploration of combination therapies to optimize their use [58].

4.2. Nanopolymers in Tissue Engineering for Skin Regeneration

In the realm of tissue engineering, nanopolymers are instrumental in creating scaffolds that closely mimic the structure and composition of the skin's native extracellular matrix (ECM). These scaffolds provide not only structural support for newly forming tissue but also deliver crucial cues that guide cell behavior, including adhesion, migration, proliferation, and differentiation. A significant approach in this area is the fabrication of nanofibrous scaffolds using techniques like electrospinning. These scaffolds possess a remarkably high surface area to volume ratio, which is highly conducive to cell attachment and proliferation, making them excellent candidates for skin tissue engineering.

Nanopolymers are also integral components of hydrogels used in tissue engineering. These hydrogels, characterized by their high-water content and inherent biocompatibility, create a physiologically relevant environment that supports cell growth and differentiation, facilitating the regeneration of skin tissue [35]. The advent of 3D bioprinting has further expanded the applications of nanopolymers in tissue engineering for skin regeneration. This advanced technology allows for the creation of complex, three-dimensional skin constructs, including skin grafts and substitutes, with precise control over their architecture and the spatial distribution of cells and biomaterials, such as nanopolymers. Bioinks, which are formulations used in 3D bioprinting, often contain nanopolymers along with living cells to print layered skin structures and even skin appendages, such as hair follicles [35].

Specific natural nanopolymers like collagen and chitosan are particularly favored in tissue engineering scaffolds for skin regeneration due to their inherent biocompatibility and bioactivity, which promote favorable cell responses and tissue integration. The concept of smart materials is also being explored in tissue engineering, where nanopolymeric scaffolds can be designed to respond to external stimuli, such as temperature or light, to actively enhance the process of tissue regeneration. Nanostructured scaffolds made from nanopolymers are capable of mimicking the nanoscale features present in the natural ECM, which leads to improved cell-matrix interactions and ultimately better outcomes in tissue regeneration. Furthermore, 3D bioprinting utilizing nanopolymeric bioinks holds the potential to create personalized skin grafts that are precisely tailored to the unique dimensions and requirements of an individual patient's wound. Combining different types of nanopolymers and other nanomaterials, such as incorporating nanoparticles within nanofibrous scaffolds or hydrogels, can result in the creation of composite materials with enhanced mechanical strength, improved biological performance, and even antimicrobial properties, further expanding their utility in tissue engineering applications [60].

4.3. Nanopolymers in Drug Delivery for Skin Regeneration

The use of nanopolymers as drug carriers has revolutionized the field of skin regeneration by offering significant advantages over traditional drug delivery methods. These advantages include improved drug stability, enhanced solubility of poorly soluble drugs, increased bioavailability at the target site, and an overall improvement in the therapeutic index. Various types of nanopolymeric drug delivery systems have been developed and explored for skin regeneration applications. Nanoparticles and nanospheres, formed from polymers like PLGA and chitosan, are capable of encapsulating and protecting a wide range of drugs, enabling their controlled release and targeted delivery to specific skin layers or cells.

Nanogels, with their cross-linked three-dimensional network structure, can release pharmaceuticals in a site-specific manner, often responding to environmental stimuli such as changes in pH or temperature, making them particularly useful for treating conditions where localized drug release is desired (Table 2). Nanofibers, typically fabricated through electrospinning, provide a large surface area for drug loading and can facilitate localized drug delivery while also offering structural support for tissue regeneration. Liposomes, composed of lipid bilayers, can effectively transport both hydrophobic and hydrophilic drugs, expanding the range of therapeutic agents that can be delivered. Dendrimers, characterized by their highly branched and well-defined structure, offer precise control over drug encapsulation and release, making them valuable tools for targeted drug delivery. Nanopolymers are being employed to deliver a diverse array of therapeutic agents aimed at enhancing skin regeneration. These include growth factors like VEGF, EGF, and PDGF, which play crucial roles in stimulating cell proliferation, differentiation, and angiogenesis, thereby accelerating tissue repair. Antibiotics are often delivered using nanopolymeric carriers to prevent and treat infections, a common complication in wounds and skin injuries [43].

Nanopolymers are powerful tools in skin regeneration due to their ability to enhance drug delivery by overcoming the skin's barrier, the stratum corneum. Their small size allows them to transport therapeutic agents, including anti-inflammatory agents and materials for gene therapy like small interfering RNA (siRNA). A key advantage is targeted drug delivery, where nanopolymer surfaces are functionalized with ligands to direct them precisely to specific cell receptors or wound sites, maximizing therapeutic effect while reducing side effects on healthy tissue [60].

The versatility of nanopolymers as drug carriers allows for multi-targeting and the delivery of combinations of drugs, paving the way for personalized medicine approaches in treating individual skin conditions. The size of the nanopolymers used is a critical factor that influences their ability to permeate the skin barrier and reach the intended target cells or tissues. Additionally, modifying the surface of nanopolymers with polyethylene glycol (PEG) can provide protection against degradation and recognition by the body's immune system, thus prolonging their circulation time and enhancing their overall therapeutic efficacy [60].

5. Innovations in Nanopolymeric Formulation and Product Development

The field of nanopolymeric formulation has witnessed significant advancements, building upon traditional methods and incorporating novel techniques to achieve greater control and functionality. Traditional methods such as emulsion polymerization and nanoprecipitation continue to be refined. Emulsion polymerization, where monomers are polymerized in an emulsion, has seen advancements allowing for better control over the resulting nanoparticle size and morphology. Nanoprecipitation, a straightforward and efficient technique, involves the rapid precipitation of a polymer from a solvent by adding a non-solvent, leading to the formation of nanoparticles [61]. Layer-by-layer assembly, a technique for creating complex nanostructures with precisely tailored surface properties, and microfluidics, a promising approach for the precise and scalable synthesis of nanoparticles [62],

also represent important areas of development. Extrusion, based on the induced precipitation of drug-loaded nanoparticles at the exit of nanopores, offers high reproducibility, while ionic gelation, involving the mixing of aqueous phases of ionic polymers like chitosan and alginate, provides a simple route to nanoparticle formation.

Emerging techniques are further expanding the capabilities of nanopolymeric formulations. The development of stimuli-responsive formulations, utilizing smart polymeric nanoparticles (PNPs) that can respond to specific environmental cues such as pH, temperature, or enzymes, represents a significant advancement [63]. This responsiveness enables controlled drug release, enhancing therapeutic outcomes. For instance, pH-sensitive polymers are being developed to achieve tumor-specific drug delivery, capitalizing on the acidic environment of tumor tissues to trigger drug release [64]. Surface modification techniques play a crucial role in tailoring the behavior of nanoparticles. PEGylation, the attachment of polyethylene glycol (PEG) to nanoparticle surfaces, significantly enhances targeting efficiency by minimizing interactions with non-target tissues and improving penetration into target areas. Beyond PEGylation, other surface modifications, such as the attachment of specific targeting ligands, are being explored to further enhance the selectivity of nanocarriers for specific cells or tissues [65].

The integration of artificial intelligence (AI) is also emerging as a powerful tool in the design of nanoparticle-based drug delivery systems. AI algorithms can analyze vast datasets to predict the optimal characteristics of nanoparticles, including size, surface chemistry, and drug release profiles, for specific therapeutic applications [63]. This computational approach has the potential to accelerate the development of tailored nanopolymeric formulations with enhanced efficacy. The ongoing progress in these formulation techniques reflects a clear trend towards achieving greater precision, control, and functionality in nanopolymer-based products.

Nanopolymers and nanocomposites are used to create high-performance materials with enhanced mechanical strength, lightness, and durability, finding applications in industries such as automotive and aerospace [66]. For instance, carbon fiber composites, incorporating nanoscale carbon fibers within a polymer matrix, offer unprecedented combinations of strength and lightness. The integration of nanoparticles like carbon nanotubes or nanoclays into polymer matrices significantly increases their strength and stiffness.

Graphene nanoplatelets added to polylactic acid (PLA) have been shown to enhance thermal conductivity by over 250%, opening new possibilities for heat transfer applications.³³ These advancements are crucial for developing lighter, stronger, and more efficient components in various engineering sectors, including packaging and electronics [66].

Nanopolymers are instrumental in the development of smart materials capable of responding to environmental changes [66]. Electrochemical and optical sensors based on nanopolymers like metal-organic frameworks (MOFs) and 2D materials are being developed for the rapid and convenient detection of various health, food quality, and environmental parameters [67]. Smart materials incorporating nanopolymers can also be used to create piezoelectric sensors for real-time structural health monitoring [66]. These innovations enable the creation of more responsive and efficient devices for a wide range of applications, from biosensing to environmental monitoring [66].

There is a growing emphasis on the development and application of nanobiopolymers derived from renewable resources as environmentally friendly alternatives to traditional synthetic polymers [67]. Examples include nanopolymers based on cellulose, starch, and lignin, which offer biodegradability and biocompatibility [68]. These sustainable nanopolymers are finding applications in various areas, including edible films, packaging materials, medical implants, and environmental pollution remediation. The shift towards biodegradable nanopolymers addresses environmental concerns and promotes a more sustainable approach to materials science.

A diverse range of biodegradable polymers is being utilized in nanoformulations to address environmental concerns. These include polylactic acid (PLA), poly(lactic-co-glycolic acid) (PLGA), chitosan, and cellulose derivatives. These polymers find applications in various sectors, such as drug delivery systems for controlled release, scaffolds for tissue engineering, and sustainable packaging solutions for food and consumer goods [69]. The development of biodegradable nanopolymers is crucial for minimizing the environmental impact of polymer-based products.

The landscape of nanopolymers includes other novel materials with unique functionalities. Self-healing polymers, capable of autonomously repairing damage, are being developed for applications requiring enhanced durability and longevity. Conductive polymers, exhibiting electrical conductivity, are finding uses in sensors, electronics, and antistatic coatings [70]. Biopolymers derived from natural sources like Aloe Vera are being explored for their environmentally friendly nature and thermal stability, with potential applications in enhanced oil recovery and other industrial processes. The continuous exploration of new nanopolymer chemistries and structures promises to yield materials with increasingly tailored and advanced properties.

Several emerging trends are poised to shape the future of nanopolymeric formulation and product development. The application of artificial intelligence (AI) and machine learning is expected to accelerate the

design and optimization of nanopolymeric formulations by enabling predictive modeling of material properties and performance. Personalized nanomedicine, tailoring nanopolymeric therapies to the specific needs of individual patients based on their genetic makeup and disease profile, is another significant trend [71]. The development of multifunctional nanoparticles that combine therapeutic delivery with diagnostic imaging capabilities (theranostics) will allow for more precise and effective disease management.

The growing global focus on sustainability is driving increased research and development of biodegradable and bio-based nanoparticles as eco-friendly alternatives. The integration of 3D printing technology into nanopharmaceutical manufacturing is also an emerging trend, enabling the fabrication of complex nanostructures and personalized drug delivery systems with greater precision and control [72]. These trends collectively point towards a future where nanopolymeric formulations will be increasingly sophisticated, personalized, sustainable, and effectively utilized across a wide range of applications.

The field of nanopolymeric formulation and product development has witnessed remarkable advancements, offering transformative potential across pharmaceuticals, cosmetics, and materials science. The ability to manipulate polymers at the nanoscale has led to the creation of products with enhanced performance, stability, and sophisticated delivery mechanisms. While challenges related to scalability, cost-effectiveness, and navigating the regulatory landscape persist, the ongoing research and emerging trends, such as AI-driven design, personalized nanomedicine, and sustainable nanoparticles, indicate a promising future. The successful examples of nanopolymer-based products already in the market highlight the practical applications and commercial viability of these innovations. As research continues to evolve, nanopolymeric formulations are poised to play an increasingly significant role in shaping the next generation of products, offering enhanced efficacy, safety, and sustainability.

6. Risks, Limitations, and Environmental Considerations of Nanopolymers

While nanoparticles offer significant therapeutic and cosmetic advantages, their widespread application raises important safety and environmental concerns that warrant careful evaluation. A balanced assessment of both benefits and risks is essential to ensure responsible development and long-term sustainability.

6.1. Potential Biological and Dermatological Risks

One primary concern relates to the potential cytotoxicity of nanopolymeric systems. Due to their small size and high surface reactivity, certain nanoparticles may induce oxidative stress, generate reactive oxygen species (ROS), and trigger inflammatory responses in skin cells. Excessive accumulation within keratinocytes or dermal fibroblasts could potentially disrupt cellular homeostasis and impair normal skin function [44,45].

Particle size, surface charge, and chemical composition significantly influence toxicity profiles. Positively charged nanoparticles, while beneficial for skin adhesion, may interact strongly with cell membranes, potentially leading to membrane destabilization. Additionally, repeated long-term exposure to nanomaterials in cosmetic formulations remains insufficiently studied, and chronic accumulation effects cannot yet be fully excluded [51].

Another concern involves unintended systemic absorption. Although most nanoparticles are designed to remain within superficial skin layers, compromised skin barriers (e.g., wounds, eczema, psoriasis) may permit deeper penetration, potentially leading to systemic distribution [25].

6.2. Regulatory and Standardization Challenges

The regulatory landscape governing nanomaterials in cosmetics and dermatology remains complex and evolving. Definitions of “nanomaterial” vary across regulatory agencies, and standardized testing protocols for nanopolymer safety assessment are still under development [61,64]. Critical parameters such as particle size distribution, aggregation behavior, biodegradability, and long-term stability must be rigorously evaluated before commercialization [65].

Furthermore, batch-to-batch reproducibility and scalability of nanopolymer production present manufacturing challenges. Variations in polymer synthesis methods may alter physicochemical properties, thereby influencing biological performance and safety outcomes.

6.3. Environmental Safety Concerns

Environmental implications of nanoparticles are increasingly recognized as an important area of investigation. During manufacturing, usage, and disposal of cosmetic products, nanopolymeric materials may enter wastewater systems and aquatic environments. Persistent or non-biodegradable nanoparticles could accumulate in soil or water ecosystems, potentially affecting microorganisms, aquatic organisms, and food chains [66].

Biodegradable polymers such as polylactic acid (PLA), poly(lactic-co-glycolic acid) (PLGA), chitosan, and cellulose derivatives offer more environmentally sustainable alternatives [68]. However, even biodegradable nanomaterials require careful assessment of degradation byproducts and their ecological impact [69].

The growing emphasis on green nanotechnology encourages the development of bio-based nanoparticles derived from renewable resources, as well as environmentally friendly synthesis methods that reduce solvent use and chemical waste.

6.4. Current Knowledge Gaps and Future Directions

Despite promising advances, several knowledge gaps remain:

- I. Long-term human exposure data are limited.
- II. Standardized toxicological models specific to dermal nanoparticles are still evolving.
- III. Environmental accumulation and ecotoxicological impacts require further investigation.

Future research should prioritize comprehensive *in vitro*, *in vivo*, and clinical safety studies, as well as lifecycle assessments to evaluate environmental sustainability. Collaboration between material scientists, toxicologists, dermatologists, and regulatory authorities will be critical to ensuring the safe and ethical integration of nanoparticles into dermatological practice.

7. Conclusions

Nanoparticles present a promising avenue for enhancing the efficacy and delivery of anti-aging compounds in both the cosmetic and medical domains. Their unique nanoscale properties offer several advantages, including improved penetration through skin barriers, targeted delivery to specific cells and tissues, controlled release of active ingredients, and enhanced stability of these often-delicate molecules. However, alongside these significant benefits, potential risks and concerns regarding the long-term effects and safety profiles of certain nanoparticles necessitate careful consideration and ongoing research.

Looking towards the future, several promising research directions can be identified. The development of novel biocompatible and biodegradable nanoparticles with precisely tailored properties for specific anti-aging targets remains a key area of focus. Further exploration of advanced delivery systems, particularly stimuli-responsive or smart nanoparticles that can release their payload on demand, holds immense potential for creating highly personalized and effective anti-aging treatments. Moreover, comprehensive safety studies, including rigorous long-term evaluations, are crucial to ensure the responsible development and application of nanoparticle-based anti-aging products and to address the existing knowledge gaps regarding their long-term impact on human health and the environment.

Author Contributions

E.E.O: conceptualization, data curation, writing—original draft preparation; N.F.S: Investigation, proofreading, initial editing; S.O.A: writing—reviewing and editing. All authors have read and agreed to the published version of the manuscript.

Funding

This research received no funding.

Institutional Review Board Statement

Not applicable.

Informed Consent Statement

Not applicable.

Data Availability Statement

Not applicable.

Acknowledgments

Special appreciation goes to all the authors who contributed to this research in one way or the other.

Conflicts of Interest

The authors declare no conflict of interest.

Use of AI and AI-Assisted Technologies

No AI tools were utilized for this paper.

References

1. Tobin, D.J. Introduction to skin aging. *J. Tissue Viability* **2017**, *26*, 37–46.
2. Hussein, R.S.; Bin Dayel, S.; Abahusseini, O.; et al. Influences on skin and intrinsic aging: Biological, environmental, and therapeutic insights. *J. Cosmet. Dermatol.* **2025**, *24*, e16688.
3. Sgarbieri, V.C.; Pacheco, M.T. Healthy human aging: Intrinsic and environmental factors. *Braz. J. Food Technol.* **2017**, *20*, e2017007.
4. Bonté, F.; Girard, D.; Archambault, J.C.; et al. Skin changes during ageing. *Subcell Biochem.* **2019**, *91*, 249 – 280.
5. Addor, F.A. Beyond photoaging: Additional factors involved in the process of skin aging. *Clin. Cosmet. Investig. Dermatol.* **2018**, *11*, 437–443.
6. Papaccio, F.; Caputo, S.; Bellei, B. Focus on the contribution of oxidative stress in skin aging. *Antioxidants* **2022**, *11*, 1121.
7. Sahawneh, P. Factors influencing skin health from within. *J. Integr. Health* **2024**, *3*, 156–163.
8. Al-Dhubaibi, M.S.; Mohammed, G.F.; Bahaj, S.S.; et al. The Role of Keratinocytes in Skin Health and Disease. *Dermatol. Rev.* **2025**, *6*, e70028.
9. Akbarian, M.; Bertassoni, L.E.; Tayebi, L. Biological aspects in controlling angiogenesis: Current progress. *Cell. Mol. Life Sci.* **2022**, *79*, 349.
10. Khalid, K.A.; Nawi, A.F.; Zulkifli, N.; et al. Aging and wound healing of the skin: A review of clinical and pathophysiological hallmarks. *Life* **2022**, *12*, 2142.
11. Salvioni, L.; Morelli, L.; Ochoa, E.; et al. The emerging role of nanotechnology in skincare. *Adv. Colloid Interface Sci.* **2021**, *293*, 102437.
12. Sabet, M. Advanced developments in carbon nanotube polymer composites for structural applications. *Iran. Polym. J.* **2025**, *34*, 917–946.
13. Yuniarsih, N.; Chaerunisaa, A.Y.; Elamin, K.M.; et al. Polymeric nanohydrogel in topical drug delivery system. *Int. J. Nanomed.* **2024**, *19*, 2733–2754.
14. Tyagi, A.; Bhardwaj, A.; Sahu, R.; et al. Emerging Nano Polymer Technologies for Synthesis and Characterization of Polymer Nanoparticles. In *Nanostructured Polymers: Synthesis and Performance*; Springer: Singapore, 2026; pp. 57–80.
15. Dutra Alves, N.S.; Reigado, G.R.; Santos, M.; et al. Advances in regenerative medicine-based approaches for skin regeneration and rejuvenation. *Front. Bioeng. Biotechnol.* **2025**, *13*, 1527854.
16. Mureed, M.; Fatima, A.; Sattar, T.; et al. The Complementary Roles of Neurological and Musculoskeletal Physical Therapy and Regenerative Medicine: A Comprehensive Review. *Medicina* **2024**, *60*, 1062.
17. Jorgensen, A.M.; Mahajan, N.; Atala, A.; et al. Advances in skin tissue engineering and regenerative medicine. *J. Burn Care Res.* **2023**, *44*, S33–S41.
18. Mazini, L.; Rochette, L.; Admou, B.; et al. Hopes and limits of adipose-derived stem cells (ADSCs) and mesenchymal stem cells (MSCs) in wound healing. *Int. J. Mol. Sci.* **2020**, *21*, 1306.
19. Hosseini, M.; Shafiee, A. Engineering bioactive scaffolds for skin regeneration. *Small* **2021**, *17*, 2101384.
20. Deng, X.; Gould, M.; Ali, M.A. A review of current advancements for wound healing: Biomaterial applications and medical devices. *J. Biomed. Mater. Res. Part B Appl. Biomater.* **2022**, *110*, 2542–2573.
21. Trovato, F.; Ceccarelli, S.; Michelini, S.; et al. Advancements in Regenerative Medicine for Aesthetic Dermatology: A Comprehensive Review and Future Trends. *Cosmetics* **2024**, *11*, 49.
22. George, J.; Sneed, K.; Pathak, Y. The skin aging process and anti-aging strategies. *Biomed. J. Sci. Tech. Res.* **2022**, *42*, 33377–33386.
23. Sharma, Y.; Ghatak, S.; Sen, C.K.; et al. Emerging technologies in regenerative medicine: The future of wound care and therapy. *J. Mol. Med.* **2024**, *102*, 1425–1450.
24. Madawi, E.A.; Al Jayoush, A.R.; Rawas-Qalaji, M.; et al. Polymeric nanoparticles as tunable nanocarriers for targeted delivery of drugs to skin tissues for treatment of topical skin diseases. *Pharmaceutics* **2023**, *15*, 657.
25. Ferraris, C.; Rimicci, C.; Garelli, S.; et al. Nanosystems in cosmetic products: A brief overview of functional, market, regulatory and safety concerns. *Pharmaceutics* **2021**, *13*, 1408.
26. Raszewska-Famielec, M.; Flieger, J. Nanoparticles for topical application in the treatment of skin dysfunctions—An overview of dermo-cosmetic and dermatological products. *Int. J. Mol. Sci.* **2022**, *23*, 15980.

27. Chavda, V.P.; Solanki, H.K.; Vaghela, D.A.; et al. Nanotechnology-Based Face Masks: Transforming the Cosmetics Landscape. *Micro* **2025**, *5*, 11.
28. Menichetti, A.; Mordini, D.; Montalti, M. Penetration of Microplastics and Nanoparticles Through Skin: Effects of Size, Shape, and Surface Chemistry. *J. Xenobiotics* **2024**, *15*, 6.
29. Chandra, J.; Hasan, N.; Nasir, N.; et al. Nanotechnology-empowered strategies in treatment of skin cancer. *Environ. Res.* **2023**, *235*, 116649.
30. Rathnasinghe, N.; Kaushani, K.G.; Jayasinghe, R.A.; et al. A review on novel nanofiber-based dermal applications: Utilization of polysaccharides. *Nanosci. Nanotechnol. Asia* **2023**, *13*, 1–5.
31. Yokota, J.; Kyotani, S. Influence of nanoparticle size on the skin penetration, skin retention and anti-inflammatory activity of non-steroidal anti-inflammatory drugs. *J. Chin. Med. Assoc.* **2018**, *81*, 511–519.
32. Shetty, K.; Sherje, A.P. Nano intervention in topical delivery of corticosteroid for psoriasis and atopic dermatitis—A systematic review. *J. Mater. Sci. Mater. Med.* **2021**, *32*, 88.
33. Xu, W.; Ling, P.; Zhang, T. Polymeric micelles, a promising drug delivery system to enhance bioavailability of poorly water-soluble drugs. *J. Drug Deliv.* **2013**, *213*, 340315.
34. Cardoza, C.; Nagtode, V.; Pratap, A.; et al. Emerging applications of nanotechnology in cosmeceutical health science: Latest updates. *Health Sci. Rev.* **2022**, *4*, 100051.
35. Jessy-Mercy, D.; Thirumalai, A.; Udayakumar, S.; et al. Enhancing Wound Healing with Nanohydrogel-Entrapped Plant Extracts and Nanosilver: An *In Vitro* Investigation. *Molecules* **2024**, *29*, 5004.
36. Baioco, K.S.; Pereira, R.; Ferreira-Gonçalves, T.; et al. Combining phototherapy and gold-based nanomaterials: A breakthrough in basal cell carcinoma treatment. *Int. J. Mol. Sci.* **2024**, *25*, 11494.
37. Bhat, B.B.; Kamath, P.P.; Chatterjee, S.; et al. Recent updates on nanocosmeceutical skin care and anti-aging products. *Curr. Pharm. Des.* **2022**, *28*, 1258–1271.
38. Babarus, I.; Lungu, I.I.; Stefanache, A. The dynamic duo: Titanium dioxide and zinc oxide in UV-protective cosmetics. *Int. J. Dev. Res.* **2023**, *13*, 63654–63659.
39. Paladini, F.; Pollini, M. Antimicrobial silver nanoparticles for wound healing application: Progress and future trends. *Materials* **2019**, *12*, 2540.
40. Vines, J.B.; Yoon, J.H.; Ryu, N.E.; et al. Gold nanoparticles for photothermal cancer therapy. *Front. Chem.* **2019**, *7*, 167.
41. Kulka, K.; Sionkowska, A. Chitosan based materials in cosmetic applications: A review. *Molecules* **2023**, *28*, 1817.
42. Asuquo, E.O.; Ukam, E.E.; Edet, E.E.; et al. Formulation and Evaluation of Banana Peel-Based Herbal Cream for Antibacterial and Antifungal Applications in Cosmetic Products. *J. Dermatol. Sci. Cosmet. Technol.* **2025**, *2*, 100106.
43. Zhang, Z.; Tsai, P.C.; Ramezanli, T.; et al. Polymeric nanoparticles-based topical delivery systems for the treatment of dermatological diseases. *Wiley Interdiscip. Rev. : Nanomed. Nanobiotechnology* **2013**, *5*, 205–218.
44. Vickram, A.S.; Richard, T. Nanopolymers in Medical Applications: Advances, Challenges, and Promising Innovations for Healthcare Enhancement. *Nano World J.* **2023**, *9*, S87–S93.
45. Ghasemiyeh, P.; Mohammadi-Samani, S. Potential of nanoparticles as permeation enhancers and targeted delivery options for skin: Advantages and disadvantages. *Drug Des. Dev. Ther.* **2020**, *14*, 3271–3289.
46. Starigazdová, J.; Nešporová, K.; Čepa, M.; et al. *In vitro* investigation of hyaluronan-based polymeric micelles for drug delivery into the skin: The internalization pathway. *Eur. J. Pharm. Sci.* **2020**, *143*, 105168.
47. Begines, B.; Ortiz, T.; Pérez-Aranda, M.; et al. Polymeric nanoparticles for drug delivery: Recent developments and future prospects. *Nanomaterials* **2020**, *10*, 1403.
48. Alves, P.L.M.; Nieri, V.; Moreli, F.D.C.; et al. Unveiling New Horizons: Advancing Technologies in Cosmeceuticals for Anti-Aging Solutions. *Molecules* **2024**, *29*, 4890.
49. Tokudome, Y.; Komi, T.; Omata, A.; et al. A new strategy for the passive skin delivery of nanoparticulate, high molecular weight hyaluronic acid prepared by a polyion complex method. *Sci. Rep.* **2018**, *8*, 2336.
50. Rohilla, S.; Rohilla, A.; Narwal, S.; et al. Global trends of cosmeceutical in nanotechnology: A review. *Pharm. Nanotechnol.* **2023**, *11*, 410–424.
51. Vaiserman, A.; Koliada, A.; Lushchak, O. Phyto-nanotechnology in anti-aging medicine. *Aging* **2021**, *13*, 10818.
52. Hamdan, S.; Pastar, I.; Drakulich, S.; et al. Nanotechnology-driven therapeutic interventions in wound healing: Potential uses and applications. *ACS Cent. Sci.* **2017**, *3*, 163–175.
53. Vanaei, S.; Parizi, M.S.; Saleemizadehparizi, F.; et al. An overview on materials and techniques in 3D bioprinting toward biomedical applications. *Eng. Regen.* **2021**, *2*, 1–18.
54. Mascarinas, A.; Harrison, J.; Boachie-Adjei, K.; et al. Regenerative treatments for spinal conditions. *Phys. Med. Rehabil. Clin.* **2016**, *27*, 1003–1017.
55. Lin, Y.; Chen, Z.; Liu, Y.; et al. Recent advances in nano-formulations for skin wound repair applications. *Drug Des. Dev. Ther.* **2022**, *16*, 2707–2728.

56. Freitas, C.S.; Pereira, P.R.; Cardoso, R.V.; et al. Antimicrobial and wound healing potential of naphthoquinones encapsulated in nanochitosan. *Front. Bioeng. Biotechnol.* **2024**, *11*, 1284630.
57. Kusnadi, K.; Herdiana, Y.; Rochima, E.; et al. Collagen-Based Nanoparticles as Drug Delivery System in Wound Healing Applications. *Int. J. Nanomed.* **2024**, *19*, 11321–11341.
58. Kosksi, T.; Bustos-Salgado, P.; Rejeb, M.; et al. Development of Polymeric Nanoparticles Loaded with Phlomis crinita Extract: A Promising Approach for Enhanced Wound Healing. *Int. J. Mol. Sci.* **2025**, *26*, 2124.
59. Amor, I.B.; Emran, T.B.; Hemmami, H.; et al. Nanomaterials based on chitosan for skin regeneration: An update. *Int. J. Surg.* **2023**, *109*, 594–596.
60. Somkuwar, S.R.; Chaudhary, R.R.; Ramteke, P.W. Nanopolymer: Overview, innovation and applications. *Polym. Sci. Peer Rev. J.* **2022**, *3*, 12–23.
61. Ljubimova, J.Y.; Holler, R. Biocompatible nanopolymers: The next generation of breast cancer treatment? *Nanomedicine* **2012**, *7*, 1467–1470.
62. Souto, E.B.; Silva, G.F.; Dias-Ferreira, J.; et al. Nanopharmaceutics: Part II: Production scales and clinically compliant production methods. *Nanomaterials* **2020**, *10*, 455.
63. Ali, F.; Neha, K.; Parveen, S. Current regulatory landscape of nanomaterials and nanomedicines: A global perspective. *J. Drug Deliv. Sci. Technol.* **2023**, *80*, 104118.
64. Eltaib, L. Polymeric Nanoparticles in Targeted Drug Delivery: Unveiling the Impact of Polymer Characterization and Fabrication. *Polymers* **2025**, *17*, 833.
65. Mugundhan, S.L.; Mohan, M. Nanoscale strides: Exploring innovative therapies for breast cancer treatment. *RSC Adv.* **2024**, *14*, 14017–14040.
66. Rathod, A.V.; Katekar, V.A.; Deshmukh, S.P. A review: Recent advancement in the formulation and evaluation of the nanoparticles and its application. *GSC Biol. Pharm. Sci.* **2023**, *25*, 116–122.
67. Callister, W.D.; Rethwisch, D.G. *Fundamentals of Materials Science and Engineering*; John Wiley & Sons: Hoboken, NJ, USA, 2022; p. 29.
68. García, J.M. Trends and challenges in polymer sensors. *Sens. Polym.* **2024**, *14*, 803–828.
69. Abuzreda, A. Nanopolymers types, classification, properties, and uses. *Adv. Environ. Waste Manag. Recycl.* **2023**, *6*, 402–408.
70. Bharathy, P.; Thanikachalam, P.V. Recent Advances and Future Prospects in Polymer-Mediated Drug Delivery Systems: A Comprehensive Review. *Int. J. Drug Deliv. Technol.* **2024**, *14*, 1896–1907.
71. Malik, S.; Muhammad, K.; Waheed, Y. Nanotechnology: A revolution in modern industry. *Molecules* **2023**, *28*, 661.
72. Peter, J. Advancements in Drug Formulation: Innovations Shaping the Future of Medicine. *J. Pharm. Res. Clin. Pract.* **2023**, *6*, 62–65.